

WOVEN WIRE CLOTH SCREEN

Field of the invention

This invention concerns woven wire cloth screens for filtering liquids from a mixture of solids and liquids, particularly but not exclusively drilling muds. Typically such screens are located in a vibratory shaker to assist in separating the constituents of the mud and to cause the solids left on the wire cloth of the screen to migrate to one end thereof for discharge and collection.

Background

Certain strata produce relatively large highly abrasive particles when drilled, and screens have been found to fail prematurely in use, when drilling through such material. Thus instead of a screen lasting for up to several days before abrasion ruptures the wire cloth, failure has occurred within a few hours.

It is an object of the present invention to provide an improved design of woven wire cloth screen, which overcomes this problem.

Summary of the invention

According to the present invention, in a woven wire cloth screen in which at least one fine mesh cloth overlies a coarser mesh backing cloth, an additional coarser mesh cloth is secured over the fine mesh cloth, whose mesh and wire size at least are selected so as in general to prevent relatively large abrasive particles from making contact with the fine mesh cloth.

Best Available Copy

In general the tension in wires making up one cloth is arranged to be different from the tension in the wires making up the other cloth and where there are three or more cloths, different tensions may exist in each of the cloths. However it is to be understood that the invention is not limited to arrangements in which each cloth has a different tension from the other(s) and the cloths (or some of them) may have the same tension if appropriate.

The tension of the said additional cloth can affect its performance, and the tension in the mesh of this additional cloth is selected so that it will perform its protective function and not adversely affect the vibration of the fine mesh cloth (or cloths) therebelow.

In general the tension in the additional coarse mesh cloth is greater than that in the fine mesh cloth(s), typically approximately twice the tension in the latter.

Preferably two fine mesh cloths overlie the backing cloth so that one fine mesh cloth is sandwiched between the upper fine mesh cloth and the backing cloth, and the mesh size of the cloth which is so sandwiched is very close to the mesh size of the said upper cloth, and in use assists in de-blinding the upper cloth due to relative vibrational movement between it and the lower fine mesh cloth, and the additional coarser mesh cloth overlies the upper fine mesh cloth.

The mesh size of the additional cloth must be selected with care since if the mesh openings are too large, correspondingly large sharp particles can reach and damage the upper cloth therebelow. Likewise if the openings in the additional cloth are too large the additional cloth may not allow steady migration of separated solids over the screen in use, resulting inter alia in local overloading and failure.

The additional cloth may to advantage have rectangular mesh openings such that for example the openings in the weave are twice as long in one direction as in the other. In general the larger dimensions of the openings in the weave should run parallel to the direction in which separated solids migrate over the surface of the screen in use.

Typically the cloths are stretched over and bonded to a rigid frame and in general such frames are rectangular (although other shaped frames can be used). A screen having a rectangular frame will be referred to as a rectangular screen and in general rectangular screens are normally operated so that the longer dimension of the screen is parallel to the direction in which separated solids migrate over the screen. Therefore as a general rule, where the screen includes a generally rectangular frame to which the cloths are secured, the said additional cloth is fitted to the screen frame so that the larger dimensions of the openings in the weave are parallel to the longer edges of the frame.

Where a screen frame is for example square, and the cloths have rectangular openings, the cloths are preferably fitted to the frame so that the larger dimensions of the mesh openings are parallel to one edge of the frame and the latter is mounted in a shaker so that the direction of solids migration over the screen in use is parallel to the said one edge of the frame.

Examples of improved screens

In a preferred screen having a single fine mesh cloth the three cloths may be as follows:-

Backing cloth: 30# x 0.280mm diameter S/S wire
Fine mesh cloth: 180# x 0.030mm diameter S/S wire
Additional top cloth: 30# x 60# x 0.160mm diameter S/S wire.

In another preferred screen having two fine mesh cloths, the four cloths may be as follows:-

Backing cloth: 30# x 0.280mm diameter S/S wire
Upper fine mesh: 180# x 0.030mm diameter S/S wire
Lower fine mesh: 160# x 0.036mm diameter S/S wire
Additional top cloth: 30# x 60# x 0.160mm diameter S/S wire

Tensions in the wire mesh cloths is normally achieved using pneumatically powered rams acting on clamps which grip the edges of the cloths. If (as is usual) all the rams are of the same size, the tensions imparted to the cloths will be proportional to the air pressure applied to the rams acting on the different cloths.

In the case of a three-cloth screen the pressures applied to the three sets of rams may be in the following ratios:-

Backing mesh	Fine mesh	Additional top mesh
2.0	1.0	1.9

In the case of a four cloth screen the pressures applied to the different sets of rams may be in the following ratios:

Backing mesh	Lower fine mesh	Upper fine mesh	Additional top mesh
2.0	1.0	1.0	1.9

Where the two fine mesh cloths are to have the same tension (as in this last example) they can be tensioned together using the same set of clamps and rams.

If however the tension in one fine mesh cloth is to be different from that in the other fine mesh cloth, then a further set of rams and clamps will be needed to allow each cloth to be tensioned independently of the other.

A screen constructed in accordance with the invention has proved more durable than screens not having the additional cloth when sifting drilling mud recovered from a sea-bed drilling operation as the drill is progressing through sub-sea strata composed of Utsira sand.

The invention also lies in a method of making a woven wire cloth screen which will withstand highly abrasive large particles such as obtained when drilling through Utsira sand, in which a support frame is located in a jig, a coarse backing cloth is stretched over the frame and secured between clamping jaws along all four edges and then tensioned by moving all the clamps relatively outwardly by pneumatic rams, similarly stretching a fine mesh wirecloth over the first cloth and similarly tensioning it by means of a second set of clamps and rams, similarly stretching an additional coarse mesh cloth over the fine mesh cloth and tensioning it by means of a third set of clamps and rams, thereafter securing the cloths to the support frame under pressure, releasing the pressure, opening the clamping jaws, trimming surplus wirecloth back to the frame and removing the finished screen from the jig.

If two fine mesh cloths are required the second fine mesh cloth may be laid over the first fine mesh cloth before the top coarse cloth is applied. Both fine mesh cloths can be clamped with the same set of jaws and rams, or a further set of jaws and rams may be provided for tensioning the second fine mesh cloth. Where only one set of jaws is provided for the two fine mesh cloths the two cloths will have the same tension, but where a separate set of jaws and rams are provided the tension in the second fine mesh cloth may be different from that in the first fine mesh cloth.

If slippage is noted where two fine mesh cloths are clamped in the same set of jaws, the method may include the step of inserting a strip of coarser mesh cloth between the two layers locally between the clamping jaws, to assist in gripping the two fine mesh layers between the jaws.

The invention will now be described by way of example with reference to the accompanying drawing in which the single Figure, Fig 1, illustrates to an enlarged scale in plan view from above, a small part of a fine mesh cloth 10 overlaid by a coarse mesh cloth 12. The mesh size of 12 is such as to prevent, in general, relatively large abrasive particles from making contact with the fine mesh cloth 10. In the drawing, a backing cloth (which would be below the fine mesh cloth) has been omitted, for clarity.

All of the cloths are secured in position in manner known per se to a relatively rigid frame (not shown) by bonding to a thermoplastic material from which the screen is constructed or which covers a metal or other inner core, so as to form a screen for use in a sieving machine such as a shale shaker used to separate solids from drilling mud retrieved from down-hole during oil or gas well drilling operations.

An example of such a screen and frame and its manner of manufacture is illustrated and described in GB Patent Specification No. 2,322,590 and GB Patent Application No. 0226338.2.

CLAIMS

1. A woven wire cloth screen in which at least one fine mesh cloth overlies a coarser mesh backing cloth and an additional coarser mesh cloth is secured over the fine mesh cloth, whose mesh and wire size at least are selected so as in general to prevent relatively large abrasive particles from making contact with the fine mesh cloth.
2. A screen as claimed in claim 1 wherein the tension in wires making up one cloth is different from the tension in the wires making up at least one of the other cloths.
3. A screen as claimed in claim 2 wherein a different tension exists in the wires making up each of the cloths.
4. A screen as claimed in claim 1 wherein the tension in the wires of each of the cloths is the same.
5. A screen as claimed in claim 1 wherein the tension in the additional coarse mesh cloth is greater than that in the fine mesh cloth(s).
6. A screen as claimed in claim 5 wherein the tension in the additional coarse mesh cloth is approximately twice the tension in the fine mesh cloths.
7. A screen as claimed in any of claims 1 to 6 wherein two fine mesh cloths overlie the backing cloth so that one fine mesh cloth is sandwiched between the upper fine mesh cloth and the backing cloth, and the mesh size of the cloth which is so sandwiched is very close to the mesh size of the said upper fine mesh cloth, and in use assists in de-blinding the upper cloth due to relative vibrational movement between it and the lower fine mesh cloth, and the additional coarser mesh cloth overlies the upper fine mesh cloth.

8. A screen as claimed in any of claims 1 to 7 wherein the additional cloth has rectangular mesh openings.
9. A screen as claimed in claim 8 wherein the rectangular openings in the weave are twice as long in one direction as in the other.
10. A screen as claimed in claim 8 or 9 wherein the larger dimensions of the openings in the weave run parallel to the direction in which separated solids migrate over the surface of the screen in use.
11. A screen as claimed in any of claims 1 to 10 wherein the cloths are stretched over and bonded to a rigid frame.
12. A screen as claimed in claim 11 wherein the rigid frame is rectangular.
13. A screen as claimed in claim 12 which in use is arranged so that the longer dimension of the screen is parallel to the direction in which separated solids migrate over the screen.
14. A screen as claimed in any of claims 8 to 13 wherein the additional cloth is fitted to the frame so that the larger dimensions of the openings in the weave are parallel to the longer edges of the frame.
15. A screen as claimed in claim 1 having a single fine mesh cloth sandwiched between backing cloth and overlying additional coarse mesh cloth in which the backing cloth is 30# x 0.280mm diameter S/S wire, the fine mesh cloth is 180# x 0.030mm diameter S/S wire and the additional top cloth is 30# x 60# x 0.160mm diameter S/S wire.
16. A screen as claimed in claim 7 wherein the backing cloth is 30# x 0.280mm diameter S/S wire, the upper fine mesh is 180# x 0.030mm diameter S/S wire, the lower fine

mesh is 160# x 0.036mm diameter S/S wire, and the additional top cloth is 30# x 60# x 0.160mm diameter S/S wire.

17. A method of making a screen as claimed in claim 1 wherein the cloths are in turn laid over a rigid frame to which they are to be bonded and the tension in the wire mesh cloths is achieved using pneumatically powered rams acting on clamps which grip the edges of the cloths, wherein all the rams are of the same size and different tensions are imparted to the cloths by supplying air at differing pressures to the rams acting on the different cloths.
18. A method as claimed in claim 17 when employed to make a screen as claimed in claim 1 in which the pressures applied to the three sets of rams are in the following ratios, backing mesh rams 2.0, fine mesh rams 1.0, and additional top mesh rams 1.9.
19. A method as claimed in claim 17 when employed to make a screen as claimed in claim 7 in which the pressures applied to the rams are in the following ratios, backing mesh rams 2.0, lower fine mesh rams 1.0, upper fine mesh rams 1.0, and additional top mesh rams 1.9.
20. A method as claimed in claim 19 wherein the two fine mesh cloths are clamped and tensioned together, using one set of clamps and rams.
21. A method of making a woven wire cloth screen which will withstand highly abrasive large particles such as obtained when drilling through Utsira sand, in which a support frame is located in a jig, a coarse backing cloth is stretched over the frame and secured between clamping jaws along all four edges and then tensioned by moving all the clamps relatively outwardly by pneumatic rams, similarly stretching a fine mesh wirecloth over the first cloth and similarly tensioning it by means of a second set of clamps and rams, similarly stretching an additional coarse mesh cloth over the fine mesh cloth and tensioning it by means of a third set of clamps and rams, thereafter securing the cloths to the support frame under pressure, releasing the pressure, opening

the clamping jaws, trimming surplus wirecloth back to the frame and removing the finished screen from the jig.

22. A method as claimed in claim 21 wherein a second fine mesh cloth is laid over the first fine mesh cloth before the top coarse cloth is applied.
23. A method as claimed in claim 22 wherein the two fine mesh cloths are clamped using the same set of jaws and rams.
24. A screen as claimed in any of claims 1 to 16 when fitted to and used to sift drilling mud recovered from a sea-bed drilling operation progressing through sub-sea strata composed of Utsira sand.




Fig 1

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/03/04531

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01D29/01 B01D33/00 B07B1/46 B07B1/48

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01D B07B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 958 236 A (BAKULA JOHN J) 28 September 1999 (1999-09-28)	1,4,7, 11,12
Y	column 9, lines 44-62; figures 1,6,22	2,3,17
X	US 6 454 099 B1 (GRICHAR CHARLES N ET AL) 24 September 2002 (2002-09-24)	1,4,7, 11,12
Y	column 11, line 67 - column 12, line 5; figures 1A,13C	2,3,17
X	US 5 221 008 A (DERRICK JR H WILLIAM ET AL) 22 June 1993 (1993-06-22)	1,4,7, 11,12
Y	column 5, lines 3-29; figures 1,3	2,3,17
Y	GB 2 322 590 A (UNITED WIRE LTD) 2 September 1998 (1998-09-02) abstract page 6, line 16 - page 7, line 20; claims 28-30	2,3,17
	-/-	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

11 February 2004

Date of mailing of the international search report

17/02/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hoffmann, A

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/GB93/04531

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 169 698 A (THULE UNITED LTD) 29 January 1986 (1986-01-29) page 9, line 20 - page 12, line 6	2,3
Y	GB 2 308 315 A (UNITED WIRE LTD) 25 June 1997 (1997-06-25) page 2, column 26 - page 3, column 7	2,3
A	WO 99/24144 A (ITS DRILLING SERVICES LTD ; MORRIS RONALD G (GB); RENNIE LYALL (GB)) 20 May 1999 (1999-05-20) page 3, lines 11-32	2,3
A	US 5 927 511 A (BALTZER TERRY L ET AL) 27 July 1999 (1999-07-27) column 5, lines 57-67; figures 10,11	17
A	US 4 696 751 A (EIFLING DENNIS R) 29 September 1987 (1987-09-29) column 2, line 60 - column 3, line 27; figures 1,2	8,9

INTERNATIONAL SEARCH REPORT

on patent family members

International Application No

PCT/G.../04531

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
US 5958236	A	28-09-1999	US	5783077 A		21-07-1998
			US	5417859 A		23-05-1995
			US	5417858 A		23-05-1995
			US	6053332 A		25-04-2000
			US	6340089 B1		22-01-2002
			US	2002033358 A1		21-03-2002
			US	6000556 A		14-12-1999
			US	5876552 A		02-03-1999
			AU	690096 B2		23-04-1998
			AU	6084494 A		15-08-1994
			CA	2152602 A1		21-07-1994
			DE	69420701 D1		21-10-1999
			DE	69420701 T2		02-03-2000
			DK	680385 T3		31-01-2000
			EP	0680385 A1		08-11-1995
			ES	2135563 T3		01-11-1999
			WO	9415723 A1		21-07-1994
			US	5417793 A		23-05-1995
			AU	693086 B2		25-06-1998
			AU	6023194 A		15-08-1994
			AU	714591 B2		06-01-2000
			AU	6593998 A		09-07-1998
			CA	2152610 A1		21-07-1994
			DE	69421381 D1		02-12-1999
			DE	69421381 T2		06-04-2000
			DK	680386 T3		24-01-2000
			EP	0680386 A1		08-11-1995
			ES	2137356 T3		16-12-1999
			WO	9415724 A1		21-07-1994
			US	5720881 A		24-02-1998
			US	5868929 A		09-02-1999
			US	5944993 A		31-08-1999
US 6454099	B1	24-09-2002	US	6152307 A		28-11-2000
			US	6267247 B1		31-07-2001
			US	5988397 A		23-11-1999
			US	5971159 A		26-10-1999
			US	5385669 A		31-01-1995
			US	5392925 A		28-02-1995
			US	5598930 A		04-02-1997
			US	5490598 A		13-02-1996
			US	6565698 B1		20-05-2003
			US	6283302 B1		04-09-2001
			US	6401934 B1		11-06-2002
			AU	7433600 A		17-04-2001
			CA	2381726 A1		22-03-2001
			EP	1212130 A1		12-06-2002
			EP	1270058 A2		02-01-2003
			WO	0119492 A1		22-03-2001
			NO	20020854 A		08-05-2002
			US	6629610 B1		07-10-2003
			US	6581781 B1		24-06-2003
			US	2002000399 A1		03-01-2002
			US	2002079251 A1		27-06-2002
			AU	2303100 A		01-08-2000
			CA	2359346 A1		20-07-2000
			EP	1140379 A1		10-10-2001
			WO	0041822 A1		20-07-2000

INTERNATIONAL SEARCH REPORT

on patent family members

International Application No

PCT/03/04531

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6454099	B1	NO 20012900 A	31-08-2001
		US 2003038061 A1	27-02-2003
		US 6290068 B1	18-09-2001
		US 6325216 B1	04-12-2001
		US 6269953 B1	07-08-2001
		US 6443310 B1	03-09-2002
		US 6450345 B1	17-09-2002
		US 2002043485 A1	18-04-2002
		AU 1159600 A	22-05-2000
		CA 2349538 A1	11-05-2000
		WO 0025943 A2	11-05-2000
		EP 1128914 A2	05-09-2001
		NO 20010776 A	05-04-2001
		US 6371302 B1	16-04-2002
		AU 8447898 A	10-02-1999
		WO 9903601 A1	28-01-1999
		GB 2341567 A ,B	22-03-2000
		NO 995669 A	15-03-2000
		US 6302276 B1	16-10-2001
		AT 257044 T	15-01-2004
		AT 198168 T	15-01-2001
		AU 1799397 A	28-08-1997
		CA 2240693 A1	14-08-1997
		DE 69703730 D1	25-01-2001
		EP 1002588 A1	24-05-2000
US 5221008	A	22-06-1993	NONE
GB 2322590	A	02-09-1998	GB 2337019 A ,B
		AT 256509 T	10-11-1999
		AT 252949 T	15-01-2004
		AT 237409 T	15-11-2003
		AU 724886 B2	15-05-2003
		AU 6304498 A	05-10-2000
		BR 9807644 A	18-09-1998
		DE 69813521 D1	22-02-2000
		DE 69813521 T2	22-05-2003
		DE 69819371 D1	24-12-2003
		DE 69820683 D1	04-12-2003
		DK 1205263 T3	29-01-2004
		DK 963261 T3	05-01-2004
		EP 1205261 A2	02-06-2003
		EP 1205262 A2	15-05-2002
		EP 1205263 A2	15-05-2002
		EP 1205264 A2	15-05-2002
		EP 1205265 A2	15-05-2002
		EP 0963261 A1	15-12-1999
		ES 2197462 T3	01-01-2004
		WO 9837988 A1	03-09-1998
		HK 1024200 A1	08-08-2003
		JP 2001513020 T	28-08-2001
		NO 994245 A	01-09-1999
		US 2002088531 A1	11-07-2002
		US 2002088532 A1	11-07-2002
		US 2002088747 A1	11-07-2002
		US 2002096470 A1	25-07-2002
		US 2002113043 A1	22-08-2002
		US 6675975 B1	13-01-2004

INTERNATIONAL SEARCH REPORT

on patent family members

International Application No

PCT/GB93/04531

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2322590	A	ZA 9801678 A	27-08-1999
		ZA 9902852 A	27-08-1999
EP 0169698	29-01-1986	AU 573868 B2	23-06-1988
		AU 4520185 A	23-01-1986
		CA 1274189 A1	18-09-1990
		EP 0169698 A2	29-01-1986
		ES 296761 U	16-01-1988
		GB 2161715 A ,B	22-01-1986
		GB 2162091 A ,B	29-01-1986
		GB 2175222 A ,B	26-11-1986
		JP 2556678 B2	20-11-1996
		JP 61038607 A	24-02-1986
		NO 852856 A ,B,	22-01-1986
		US 4728422 A	01-03-1988
		ZA 8505410 A	26-03-1986
		ES 8706467 A1	16-09-1987
GB 2308315	A	25-06-1997	NONE
WO 9924144	A	20-05-1999	GB 2346817 A ,B
			WO 9924144 A1
			NO 20002402 A
US 5927511	A	27-07-1999	AU 4000499 A
			CA 2332539 A1
			EP 1098688 A1
			WO 0000264 A1
US 4696751	A	29-09-1987	GB 2194167 A ,B

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.